

PRODUCT DATA SHEET

Sika MonoTop®-4012

High performing more sustainable R4 concrete repair mortar

PRODUCT DESCRIPTION

Sika MonoTop®-4012 is a one-part, cementitious, fibre reinforced, low shrinkage repair mortar. It contains recycled raw materials and can reduce the carbon footprint application activity calculations.

USES

Sika MonoTop®-4012 may only be used by experienced professionals.

Sika MonoTop®-4012 is used to repair all types of reinforced concrete structures and components for:

- Buildings.
- Civil engineering structures.
- Dams.
- Marine structures.
- Suitable for interior or exterior applications.
- Sewage and waste water treatment plants.

The product is used for:

- Restoration work (Principle 3, method 3,1 and 3,3 of EN 1504-9). Repair of spalling and damaged concrete in infrastructure and superstructure works.
- Structural strengthening (Principle 4, method 4,4 of EN 1504-9). Increasing the bearing capacity of the concrete structure by adding mortar.
- Preserving or restoring passivity (Principle 7, method 7,1 and 7,2 of EN 1504-9) - Increasing cover with additional mortar and replacing contaminated or carbonated concrete

Please note:

- The Product may only be used by experienced professionals.

CHARACTERISTICS / ADVANTAGES

- Uses recycled raw materials.
- Layer thickness 6 to 120 mm.
- Sulphate resistant.
- Hand and machine application (wet spray technique).

- Easy to apply.
- Very low shrinkage.
- Dust reduced.
- Good resistance to sea water.
- Does not require a bonding primer.
- Low permeability.
- EuroClass A1 fire rating.
- Class R4 of EN 1504-3.
- Resistant to sulfuric acid attack (exposure classes XWW1 and XWW3).

ENVIRONMENTAL INFORMATION

- Conforms with LEED v4 MR credit: Building product disclosure and optimisation — Environmental Product Declarations (option 1).
- Conforms with LEED v4 MR credit: Building product disclosure and optimisation — Sourcing of raw materials (option 2).
- Conforms with LEED v4 MR credit: Building product disclosure and optimisation — Material ingredients (option 2).
- Specific Environmental Product Declaration (EPD) in accordance with EN 15804. EPD independently verified by BRE Global.

APPROVALS / STANDARDS

- CE marking and declaration of performance based on EN 1504-3 Products and systems for the protection and repair of concrete structures — Structural and non-structural repair.
- Specific electrical resistivity DIN EN ISO 12696, Sika MonoTop®-4012, OST.
- Tensile bond strength after vibrational stress DAFStb guideline, Sika MonoTop®-4012, Kiwa, Test report No. P 11864-1-E.
- Sulphate Resistance ÖNORM B 3309-1, Sika MonoTop®-4012, HARTL, No. 013108/2.

PRODUCT INFORMATION

Chemical Base	Sulphate resistant and replacement cement, selected aggregates and additives.	
Packaging	25 kg bag	
Shelf Life	12 months from date of production	
Storage Conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C. Protect the product from direct sunlight. Always refer to packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.	
Appearance / Colour	Grey powder	
Maximum Grain Size	D _{max} : 2 mm	
Soluble Chloride Ion Content	≤ 0,05 %	(EN 1015-17)

TECHNICAL INFORMATION

Abrasion Resistance	Wear Resistance Böhme, wet procedure	< 12 cm ³ /50 cm ²	(DIN 52108)
Compressive Strength	Class R4		(EN 1504-3)
	Time	Compressive strength	(EN 12190)
	1 day	~19 MPa	
	7 days	~43 MPa	
	28 days	~56 MPa	
Modulus of Elasticity in Compression	≥ 20 GPa		(EN 13412)
Flexural Strength	Time	Tensile strength in flexure	(EN 12190)
	1 day	~4.4 MPa	
	7 days	~7.0 MPa	
	28 days	~8.0 MPa	
Tensile adhesion strength	≥ 2.0 MPa		(EN 1542)
Shrinkage	~500 µm/m (+20 °C / 65 % relative humidity at 28 days)		(EN 12617-4)
Restrained Shrinkage / Expansion	≥ 2.0 MPa		(EN 12617-4)
Electrical Resistivity	~32 kΩ·cm at 100% relative humidity @ 20°C		(ISO 12696)
Thermal Compatibility	≥ 2.0 MPa (Part 1 - Freeze-Thaw)		(EN 13687-1)
Capillary Absorption	≤ 0.5 kg·m ⁻² ·h ^{-0.5}		(EN 13057)
Water Penetration under Pressure	~10 mm		(EN 12390-8)
Chloride Ion Diffusion Resistance	Low - < 2000 coulombs		(ASTM C 1202)
	Chloride diffusion coefficient: 4,8 x 10 ⁻¹² m ² /s		(EN 12390-11)
Chloride Ion Diffusion Resistance	4.8 x 10 ⁻¹² m ² /s		(EN 12390-11)
Carbonation Resistance	dk ≤ control concrete MC (0,45)		(EN 13295)
Reaction to Fire	EuroClass A1		(EN 1504-3)

SYSTEM INFORMATION

System Structure	Layer	Product	Function
	Bonding primer / Reinforcement corrosion protection	Sika MonoTop®-1010	Normal use
		SikaTop® Armatec®-110 EpoCem	Demanding requirements
	Concrete repair mortar	Sika MonoTop®-4012	High strength requirements
	Levelling mortar	Sika MonoTop®-3020 Sikagard®-720 Epo-Cem®	Normal use Demanding requirements

APPLICATION INFORMATION

Mixing Ratio	3,75 to 3,9 L of water for a 25 kg bag		
Fresh mortar density	~2.1 kg/L		
Consumption	~1.9 kg/m ² /mm Note: Consumption data is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.		
Yield	25 kg of powder yields ~13.7 L of mortar		
Layer Thickness	Orientation	Minimum	Maximum
	Horizontal	6 mm	120 mm
	Vertical	6 mm	85 mm (120 mm in localised areas)
	Overhead	6 mm	30 mm (50 mm in localised areas)
Product Temperature	Maximum	+30 °C	
	Minimum	+5 °C	
Ambient Air Temperature	Maximum	+30 °C	
	Minimum	+5 °C	
Substrate Temperature	Maximum	+30 °C	
	Minimum	+5 °C	
Pot Life	~60 minutes at +20 °C		

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

- Site Handbook 'Repair of Concrete Structures: Patch Repair and Spray Applications'.
- Sika Method Statement: Concrete Repair Using Sika MonoTop® System.
- Recommendations provided in EN 1504-10.

LIMITATIONS

- Avoid application in direct sun and/or strong winds.
- Do not add water over recommended dosage.
- Apply only to stable, prepared substrates.
- Do not add additional water during the surface finishing as this can cause discolouration and cracking.
- Protect freshly applied material from freezing.
- Do not 'feather edge'.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

EQUIPMENT

Select the most appropriate equipment required for the project:

SUBSTRATE PREPARATION EQUIPMENT

- Mechanical hand-held tools.
- High or ultra-high pressure water blasting equipment.

STEEL REINFORCEMENT EQUIPMENT

- Abrasive blast cleaning equipment.
- High pressure water blasting equipment.

MIXING EQUIPMENT

- Clean mixing containers.
- Small quantities: low speed electric single or double paddle mixer (< 500 rpm).
- Large quantities: Forced action mixer.

APPLICATION EQUIPMENT

- Hand applied: Plasterers hawk, trowel.
- Wet Spray: All-in-one mixing and spraying machine or separate spraying machine and all associated ancillary equipment to suit application volumes.

FINISHING EQUIPMENT

- Trowel (PVC or wooden).
- Sponge.

Also refer to Site Handbook 'Repair of Concrete Structures – Patch Repair and Spray Applications'.

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete

- The substrate must be thoroughly clean, free from dust, loose material, surface contamination and material which reduce adhesion or prevent suction or wetting by repair materials.
- Remove delaminated, weak, damaged and deteriorated concrete and where necessary, sound concrete. Remove using mechanical handheld tools or high / ultra-high-pressure water blasting equipment
- Make sure sufficient concrete is removed from around corroded reinforcement to allow cleaning, corrosion protection coating (where required) and compaction of the concrete repair mortar.
- Repair surface areas must be prepared to provide simple square or rectangular layouts to avoid shrinkage stress concentrations and cracking while the repair material cures. This can also avoid structural stress concentrations from thermal movement and loading during the service life.

Steel reinforcement

- Remove rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion.
- Prepare surfaces to bright steel using abrasive blast cleaning or high-pressure water blasting equipment.

MIXING

HAND APPLIED AND WET SPRAY APPLICATION

1. Pour the minimum amount of water into a suitable clean mixing container or equipment.
2. Gradually add the powder to the water while stirring slowly.
3. Mix thoroughly for at least for 3 minutes, add additional water if necessary. Note: Do not add more water than the maximum specified amount.
4. Adjust to the required consistency to achieve a smooth consistent mix.
5. Check the consistency after every mix.

APPLICATION

IMPORTANT

Protect from frost

Protect freshly applied material from freezing and frost to prevent cracking.

IMPORTANT

Application in the direct sun or strong winds

Avoid application in direct sun, strong winds or both to reduce the risk of the product cracking.

REINFORCEMENT CORROSION PROTECTION COATING

1. Where a reinforcement coating is required, apply to the whole exposed circumference Sika MonoTop®-1010 or SikaTop® Armatec®-110 EpoCem®. Refer to the individual Product Data Sheets.

BONDING PRIMER

On a well prepared and roughened substrate or for a sprayed application, a bonding primer is generally not required.

When a bonding primer is required to achieve the required adhesion values, use Sika MonoTop®-1010 or SikaTop® Armatec®-110 EpoCem®. Refer to the individual Product Data Sheets.

REPAIR MORTAR MANUAL APPLICATION

IMPORTANT

Substrate pre-wetting

Insufficient substrate saturation prior to application will cause the mortar to not gain full mechanical properties.

1. Only apply the product to stable, prepared substrates.
2. Thoroughly pre-wet the prepared substrate for a minimum of 2 hours before application.
3. Keep the surface wet and do not allow to dry.
4. The final pre-wetted surface must achieve a dark matt appearance (i.e. saturated surface dry).

IMPORTANT

Sagging or slumping of built up layers

Allow each layer to slightly harden and remain wet before applying subsequent layers.

1. Remove excess water from within the surface pores and cavities with a clean sponge.
2. Make a scratch coat using the repair mortar.
3. Apply the scratch coat over the complete substrate surface to form a thin layer to fill surface pores or cavities.
4. IMPORTANT Do not apply as a 'feather edge'. Apply the repair mortar onto the scratch coat 'wet-on-wet' between the minimum and maximum layer thicknesses without the formation of voids.

REPAIR MORTAR SPRAYED APPLICATION - WET SPRAY IMPORTANT

Substrate pre-wetting

Insufficient substrate saturation prior to application will cause the mortar to not gain full mechanical properties.

1. Only apply the product to stable, prepared substrates.
2. Thoroughly pre-wet the prepared substrate for a minimum of 2 hours before application.
3. Keep the surface wet and do not allow to dry.
4. The final pre-wetted surface must achieve a dark matt appearance (i.e. saturated surface dry).

IMPORTANT

Sagging or slumping of built up layers

Allow each layer to slightly harden and remain wet before applying subsequent layers.

1. Remove excess water from within the surface pores and cavities with a clean sponge.
2. Place the wet mixed repair mortar into the spraying equipment.
3. Spray the repair mortar onto the pre-wetted substrate between the minimum and maximum layer thicknesses without the formation of voids.

SURFACE FINISHING

IMPORTANT

Adding water during surface finishing

Do not add water during the surface finishing as this can cause discolouration and cracking.

1. Allow mortar to surface harden.
2. Surface finish to the required surface texture using a stainless steel, steel, PVC or wooden float.

COLD WEATHER WORKING

Store bags in a warm environment and use warm water to assist with achieving strength gain and maintaining physical properties.

HOT WEATHER WORKING

Store bags in a cool environment and using cold water to assist with controlling the exothermic reaction to reduce cracking and maintaining physical properties.

CURING TREATMENT

- Protect fresh mortar immediately from premature drying using an appropriate curing method, such as curing compound, moist geotextile membrane or polythene sheet.
- Curing compounds must not be used when they could adversely affect subsequently applied products and systems.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet

Sika MonoTop®-4012
January 2024, Version 03.02
020302040030000320

SikaMonoTop-4012-en-GB-(01-2024)-3-2.pdf